5

10

CLAIMS

- 1. A polymer composition based on PVDF homopolymer and on fluorocopolymer(s), comprising, by weight:
- (A) approximately from 60 to 80 % of at least one PVDF homopolymer;
- (B) approximately from 20 to 40 % of at least one thermoplastic copolymer of vinylidene fluoride (VF_2) and of at least one other fluoromonomer, present in this copolymer in weight proportions of approximately 5 to 25 %;
- (C) approximately from 5 to 20 % [relative to the total weight of the polymers (A) and (B)] of a monomeric or polymeric plasticizer.
- 2. The composition according to Claim 1, in which the fluoromonomer is hexafluoropropylene, chlorotrifluoroethylene or trifluoroethylene.
 - 3. The composition according to Claim 1, in which the copolymer exhibits a melt index (MFI at 230 °C and under 10 kg) lower than approximately 6 g/10 min.
- 20 4. The composition according to Claim 1, in which the plasticizer includes dibutyl sebacate.
 - 5. The composition according to Claim 1, in which the plasticizer includes at least one polymeric polyester of adipic acid, of azelaic acid or of sebacic acid and of a diol, with a molecular mass of approximately 1500 to 5000.
 - 6. A pipe including at least one layer consisting of a composition according to laim 1.
 - 7. A shaped article insisting totally or partially of a composition according to Claim 1.

BIANDER

25